

MAXIMIZER CONCRETE MIX

DIVISION 03 31 00 – STRUCTURAL CONCRETE



KNOW YOUR MIX

Sakrete Maximizer Concrete Mix is a specially formulated high yield, high strength mixture of structural lightweight aggregate and cement designed for new construction or repairs where application thickness exceeds 2 inches (51 mm).



**OPEN TO FOOT TRAFFIC
24 HOURS**



**LIGHTWEIGHT
MEETS ASTM C387**



**FINAL
STRENGTH
5500
PSI**



**YIELD
AT 4" DEPTH
2.75
SQ.FT.**



C387

TECHNICAL DATA

PACKAGE SIZE	YIELD	WATER REQUIRED	SLUMP RANGE
40 lb 18.1 kg	0.46 ft ³ 0.013 m ³	0.75–1.0 gal 2.8–3.8 L	4 – 5 in 102 – 127 mm
80 lb 36.3 kg	0.92 ft ³ 0.026 m ³	1.5–2.0 gal 5.7–7.6 L	4 – 5 in 102 – 127 mm

Water demands shown are to be used as a starting reference. More water may be required to achieve desired consistency. Avoid overwatering. To determine coverage: Multiply Length (feet) x Width (feet) x Thickness (inches) and divide by 12. Then divide by the yield in the chart above to determine the numbers of bags needed. See Calculator on Sakrete.com for additional assistance. Yield and water are approximate.

COMPRESSIVE STRENGTH - 7 DAY	COMPRESSIVE STRENGTH - 28 DAY	ASTM STANDARDS
4,000 psi 28 MPa	5,500 psi 38 MPa	ASTM C387 ASTM C39

105 - 120 lbs. per cu. ft.

DIVISION 3

Structural Concrete – 03 31 00

LEED Eligibility:

Regional Materials (MR-c5)

Recycled Material (MR-c4)

PRECAUTIONS

Air, mix, and substrate temperatures should be between 40° F (4° C) and 90° F (32° C) and no rain in the forecast for 24 hours. For applications outside of this range of conditions, contact the Sakrete Technical Support Team.

- Colder temperatures or higher humidity conditions will retard set times.
- Use only clean mixing containers and tools.
- Do not over trowel.
- Do not overwater.
- Do not add anything other than clean potable water or Sakrete Bonder & Fortifier.
- Protect from freezing for 48 hours.

NOTE: Proper application and installation of all Sakrete products are the responsibility of the end user.

PREPARATION/APPLICATION

For best results, all materials should be stored between 40° F (4° C) and 90° F (32° C) 24 hours prior to installation.

**ESTIMATE
YOUR JOB**



**SAKRETE.COM/
CALCULATORS**



REFER TO:

- ACI 302.1 Guide for Concrete Flooring and Slab Construction
- ACI 304.1 Guide for Measuring, Mixing, Transportation and Placing Concrete
- ACI 305R Guide to Hot Weather Concreting
- ACI 306R Guide to Cold Weather Concreting

NOTE: It is the responsibility of the installer/appliator to ensure the suitability of the product for its intended use

MIXING

1. For projects requiring multiple bags, a mechanical mixer is recommended. Turn the mixer on and add the recommended amount of water shown in the table.
2. Empty the concrete mix into the mixer. If the mix is too stiff or dry, add additional water to achieve a forming consistency. Avoid excess water that results in a flowable mix. This will result in decreased strengths and durability.
3. Maximizer Concrete Mix can also be hand-mixed using a wheelbarrow or mortar pan. Pour the dry mix and form a crater in its center. Add water (refer to table) to the crater.
4. Mix using a garden hoe or shovel until a stiff forming consistency is achieved.
5. Ensure that the concrete is mixed thoroughly with no dry pockets/lumps.
6. The recommended slump is 4" to 5" (102 mm to 127 mm) to achieve the published strengths.

APPLICATION: FLATWORK (SLABS, SIDEWALKS, WALKWAYS, ETC.)

1. Stake out the area where the concrete will be placed and remove all soil, grass, debris, etc.
2. For improved drainage, place several inches of gravel into the excavated area. Remember to allow enough depth for both the gravel and a minimum of 4" (102 mm) of concrete.
3. Pre-treat forms with a release agent to prevent water absorption and for the ease of removal.
4. Place forms in the desired area, ensuring that they are level, square, and that all corners are sealed so no material can outflow.
5. Place the mixed concrete into the forms to full depth.
6. Fully fill the form, working the mix into corners and compacting to minimize voids.
7. Using a straight edge, strike the surface level with the top of the forms using a sawing motion.
8. Use a float to smooth the surface and remove any imperfections. Use an edging tool to smooth the edges along the forms.
9. Using a concrete grooving tool, cut joints into the concrete every 3-4 ft. (.9-1.2 m). Expansion joints should be placed a minimum of every 8 ft. x 12 ft. in each direction and must extend through the entire depth of the slab.
10. Once concrete has stiffened slightly, a broom finish can be applied. Forms can also be removed once the material has set (after approx. 24 hours).

APPLICATION: POSTS AND POLES

1. If the pole or post will be load-bearing, consult with your local building code requirements before proceeding.
2. Dig a hole to the required depth and diameter. A general rule of thumb is that the depth should be 1/3 the length of the post or pole and the diameter should be 3 times that of the pole or post).
3. Place 3-4 inches (102 mm to 152 mm) of gravel at the base to help with drainage.
4. Place the post or pole in the center of the hole.
5. Level and support the post or pole in place.
6. Fill the hole with mixed concrete and consolidate by rodding.
7. Over fill the hole to slope the concrete at the surface, allowing water to drain away
8. Wait a minimum of 24 hours before posts or poles are subjected to any strain.

APPLICATION: REPAIRS (GREATER THAN 2" (51 MM) IN DEPTH)

1. Surfaces to be repaired must be sound, dimensionally stable, and clean.
2. Slick or sealed surfaces must be roughened to an ICRI CSP of 3 to 5.
3. Sides of repair area must be squared.
4. Clean all reinforcing steel to bare metal and coat with a rust preventative if not covering within 8 hours.
5. Clean and remove all loose materials and debris.
6. All surfaces that will come in contact with the concrete mix should be brought to a SSD (Surface Saturated Dry) condition.
7. Fill the repair area fully and compact the mixed material with a float to ensure there are no voids.
8. Use the float to remove any surface imperfections and to achieve the desired finish.



CURING

1. Proper curing is critical for sound results. After the concrete is set, it must be kept continuously moist for 3-5 days and kept from rain for 24 hours and from freezing for 48 hours.
2. Covering the concrete slab with plastic is a practical way to help retain moisture. Place plastic after the concrete has set. If the surface begins to appear dry, remove the plastic, moisten the surface, and replace it.
3. If temperatures are predicted to go drop below 40° F, tenting and heating the area are required.
4. New concrete can be opened to foot traffic in 24 hours and vehicular traffic in 48 hours.

SAFETY

For additional information, call the manufacturer at 866-725-7383 or Chemtrec at 800-424-9300. Refer to Safety Data Sheet (SDS) for further information. **KEEP OUT OF THE REACH OF CHILDREN.**



DANGER

HAZARD STATEMENT

Causes skin irritation. May cause an allergic skin reaction. Causes serious eye damage. May cause respiratory irritation. May cause cancer. Causes damage to organs (lungs) through prolonged or repeated exposure.

PRECAUTIONARY STATEMENTS

Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Do not breathe dust/fume/gas/mist/vapors/spray. Wash hands, forearms and face thoroughly after handling. Do not eat, drink or smoke when using this product. Use only outdoors or in a well-ventilated area. Contaminated work clothing must not be allowed out of the workplace. Wear protective gloves/protective clothing/eye protection/face protection. If on skin: Wash with plenty of water. Take off contaminated clothing and wash it before reuse. If skin irritation or rash occurs: Get medical advice/attention. If inhaled: Remove person to fresh air and keep comfortable for breathing. Call a poison center or doctor if you feel unwell. IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a poison center or doctor. If exposed or concerned: Get medical advice/attention. Store in a well-ventilated place. Keep container tightly closed. Store locked up. Dispose of contents/container to hazardous or special waste collection point, in accordance with local, regional, national and/or international regulation. Do not take internally. **KEEP OUT OF REACH OF CHILDREN.**

CONTAINS: Portland cement and Calcium Oxide

⚠ WARNING: This product can expose you to chemicals including Quartz, which are known to the State of California to cause cancer. For more information go to www.P65Warnings.ca.gov.

LIMITED PRODUCT WARRANTY

The manufacturer warrants that this product shall be of merchantable quality when used or applied in accordance with the manufacturer's instructions. This product is not warranted as suitable for any purpose other than the general purpose for which it is intended. This warranty runs for one (1) year from the dates the product is purchased. ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ON THIS PRODUCT IS LIMITED TO THE DURATION OF THIS WARRANTY. Liability under this warranty is limited to replacement or defective products or, at the manufacturer's option, refund of the purchase price. CONSEQUENTIAL AND INCIDENTAL DAMAGES ARE NOT RECOVERABLE UNDER THIS WARRANTY.

Sakrete® and the background design are registered trademarks of SAKRETE of North America LLC, 400 Perimeter Center Terrace, Ste. 1000, Atlanta, Georgia 30346 ©2023.

SAKRETE® is manufactured under license from SAKRETE of North America LLC.

For current and complete product information, contact SAKRETE Technical Services toll-free at 866-725-7383 or visit Sakrete.com